Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 03/09/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 08-08-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	06/08/2020	03/09/2020	149.71 X 149.97 X 150.54	22451	**8.354**	382.6	17.0	17.1
2	Copping Concrete	M15	06/08/2020	03/09/2020	149.88 X 150.12 X 150.07	22500	**8.256**	384.7	17.1	
3	Copping Concrete	M15	06/08/2020	03/09/2020	151.97 X 150.19 X 149.15	22824	**8.031**	391.3	17.1	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62** **Date: 13/08/2020**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 08-08-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	06/08/2020	13/08/2020	150.30 X 149.74 X 149.50	22506	**8.304**	286.2	12.7	12.3
2	Copping Concrete	M15	06/08/2020	13/08/2020	149.04 X 150.62 X 151.72	22448	**8.466**	273.9	12.2	
3	Copping Concrete	M15	06/08/2020	13/08/2020	149.41 X 149.07 X 151.70	22273	**8.253**	269.2	12.1	

The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 03/09/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 08-08-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	06/08/2020	03/09/2020	150.19 X 151.40 X 151.67	22739	8.354	408.3	18.0	17.8
2	Copping Concrete	M15	06/08/2020	03/09/2020	151.21 X 150.27 X 149.24	22723	8.256	399.0	17.6	
3	Copping Concrete	M15	06/08/2020	03/09/2020	150.32 X 151.20 X 150.01	22729	8.031	404.4	17.8	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 25/05/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 20-05-20

Customer ID : SF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Column Concrete	M25	18/05/2020	25/05/2020	150.74 X 150.29 X 150.39	22655	**8.002**	535.3	23.6	23.0
2	SF Column Concrete	M25	18/05/2020	25/05/2020	151.17 X 150.32 X 149.66	22724	**8.220**	520.4	22.9	
3	SF Column Concrete	M25	18/05/2020	25/05/2020	149.36 X 151.30 X 149.77	22599	**8.909**	504.7	22.3	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62** **Date: 15/06/2020**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 20-05-20

Customer ID : SF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Column Concrete	M25	18/05/2020	15/06/2020	149.67 X 149.75 X 149.91	22413	**8.442**	626.3	27.9	27.7
2	SF Column Concrete	M25	18/05/2020	15/06/2020	151.39 X 149.07 X 149.58	22567	**8.207**	604.6	26.8	
3	SF Column Concrete	M25	18/05/2020	15/06/2020	150.94 X 149.54 X 149.95	22571	**8.732**	643.1	28.5	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 10/06/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 05-06-20

Customer ID : SF Tie Beam Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Tie Beam Concrete	M25	03/06/2020	10/06/2020	149.58 X 150.98 X 150.03	22583	**8.002**	528.3	23.4	22.7
2	SF Tie Beam Concrete	M25	03/06/2020	10/06/2020	150.20 X 150.34 X 150.06	22581	**8.220**	503.8	22.3	
3	SF Tie Beam Concrete	M25	03/06/2020	10/06/2020	151.24 X 149.78 X 151.96	22653	**8.909**	508.5	22.4	

The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 01/07/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 05-06-20

Customer ID : SF Tie Beam Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Tie Beam Concrete	M25	03/06/2020	01/07/2020	149.05 X 150.97 X 149.62	22502	**8.442**	615.2	27.3	27.7
2	SF Tie Beam Concrete	M25	03/06/2020	01/07/2020	150.30 X 150.50 X 150.69	22620	**8.207**	607.2	26.8	
3	SF Tie Beam Concrete	M25	03/06/2020	01/07/2020	150.56 X 150.90 X 149.26	22719	**8.732**	658.5	29.0	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 10/06/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 05-06-20

Customer ID : SF Tie Beam Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Tie Beam Concrete	M25	03/06/2020	10/06/2020	150.89 X 150.10 X 150.55	22648	**8.002**	543.0	24.0	23.2
2	SF Tie Beam Concrete	M25	03/06/2020	10/06/2020	150.09 X 151.88 X 149.21	22797	**8.220**	517.6	22.7	
3	SF Tie Beam Concrete	M25	03/06/2020	10/06/2020	150.16 X 150.52 X 149.12	22603	**8.909**	518.4	22.9	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL PRO Sig. Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 01/07/2020

Lab ID	:	**CP-2020-09-19-62**
Project Name	:	"Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".
Agency	:	Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/114/2017-18
Date of Receipt	:	05-06-20
Customer ID	:	SF Tie Beam Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Tie Beam Concrete	M25	03/06/2020	01/07/2020	151.54 X 149.78 X 151.37	22698	**8.442**	616.0	27.1	27.7
2	SF Tie Beam Concrete	M25	03/06/2020	01/07/2020	150.60 X 151.14 X 150.20	22762	**8.207**	614.5	27.0	
3	SF Tie Beam Concrete	M25	03/06/2020	01/07/2020	150.30 X 149.64 X 151.69	22491	**8.732**	650.4	28.9	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/06/2020

Lab ID	:	**CP-2020-09-19-62**
Project Name	:	"Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".
Agency	:	Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/114/2017-18
Date of Receipt	:	11-06-20
Customer ID	:	SF Gutter Beam Bottom Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Gutter Beam Bottom Concrete	M25	09/06/2020	16/06/2020	150.52 X 151.15 X 150.87	22750	**8.002**	532.6	23.4	22.8
2	SF Gutter Beam Bottom Concrete	M25	09/06/2020	16/06/2020	151.20 X 150.38 X 150.46	22737	**8.220**	515.8	22.7	
3	SF Gutter Beam Bottom Concrete	M25	09/06/2020	16/06/2020	150.98 X 149.27 X 149.37	22536	**8.909**	503.5	22.3	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62** **Date: 07/07/2020**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 11-06-20

Customer ID : SF Gutter Beam Bottom Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 07/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Gutter Beam Bottom Concrete	M25	09/06/2020	07/07/2020	149.13 X 150.60 X 151.84	22459	**8.442**	621.3	27.7	27.7
2	SF Gutter Beam Bottom Concrete	M25	09/06/2020	07/07/2020	149.53 X 151.92 X 149.47	22717	**8.207**	600.5	26.4	
3	SF Gutter Beam Bottom Concrete	M25	09/06/2020	07/07/2020	149.14 X 149.89 X 150.34	22356	**8.732**	646.9	28.9	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig. Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62** **Date: 16/06/2020**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 11-06-20

Customer ID : SF Gutter Beam Bottom Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Gutter Beam Bottom Concrete	M25	09/06/2020	16/06/2020	151.65 X 151.06 X 150.47	22908	**8.002**	534.2	23.3	22.5
2	SF Gutter Beam Bottom Concrete	M25	09/06/2020	16/06/2020	150.35 X 151.04 X 149.96	22709	**8.220**	500.6	22.0	
3	SF Gutter Beam Bottom Concrete	M25	09/06/2020	16/06/2020	150.17 X 149.91 X 149.86	22512	**8.909**	499.5	22.2	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62** **Date: 07/07/2020**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 11-06-20

Customer ID : SF Gutter Beam Bottom Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 07/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Gutter Beam Bottom Concrete	M25	09/06/2020	07/07/2020	149.13 X 150.60 X 151.84	22459	**8.442**	621.3	27.7	27.7
2	SF Gutter Beam Bottom Concrete	M25	09/06/2020	07/07/2020	149.53 X 151.92 X 149.47	22717	**8.207**	600.5	26.4	
3	SF Gutter Beam Bottom Concrete	M25	09/06/2020	07/07/2020	149.14 X 149.89 X 150.34	22356	**8.732**	646.9	28.9	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 19/06/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 15-06-20

Customer ID : SF Gutter Beam & Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Gutter Beam & Wall Concrete	M25	12/06/2020	19/06/2020	149.66 X 149.62 X 150.07	22392	**8.002**	536.5	24.0	23.1
2	SF Gutter Beam & Wall Concrete	M25	12/06/2020	19/06/2020	151.14 X 149.65 X 150.70	22618	**8.220**	513.7	22.7	
3	SF Gutter Beam & Wall Concrete	M25	12/06/2020	19/06/2020	149.03 X 150.93 X 150.06	22492	**8.909**	508.6	22.6	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 10/07/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 15-06-20

Customer ID : SF Gutter Beam & Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	SF Gutter Beam & Wall Concrete	M25	12/06/2020	10/07/2020	149.01 X 151.06 X 150.19	22510	**8.442**	626.6	27.8	27.8
2	SF Gutter Beam & Wall Concrete	M25	12/06/2020	10/07/2020	150.91 X 149.06 X 151.85	22493	**8.207**	601.0	26.7	
3	SF Gutter Beam & Wall Concrete	M25	12/06/2020	10/07/2020	150.75 X 151.11 X 150.62	22780	**8.732**	657.3	28.9	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig. Date. BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62**

Date: 28/07/2020

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 23-07-20

Customer ID : Below SSM Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Below SSM Concrete	M25	21/07/2020	28/07/2020	151.59 X 149.62 X 151.38	22681	8.002	531.6	23.4	22.8
2	Below SSM Concrete	M25	21/07/2020	28/07/2020	149.34 X 151.35 X 150.89	22602	8.220	512.5	22.7	
3	Below SSM Concrete	M25	21/07/2020	28/07/2020	151.21 X 151.36 X 149.46	22887	8.909	513.0	22.4	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62** **Date: 18/08/2020**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 23-07-20

Customer ID : Below SSM Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Below SSM Concrete	M25	21/07/2020	18/08/2020	151.16 X 149.99 X 151.92	22673	**8.442**	615.4	27.1	27.2
2	Below SSM Concrete	M25	21/07/2020	18/08/2020	149.85 X 151.38 X 149.54	22685	**8.207**	592.1	26.1	
3	Below SSM Concrete	M25	21/07/2020	18/08/2020	150.81 X 151.69 X 149.23	22876	**8.732**	647.5	28.3	

The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-09-19-62** **Date: 28/07/2020**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 23-07-20

Customer ID : Below SSM Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Below SSM Concrete	M25	21/07/2020	28/07/2020	150.83 X 150.22 X 151.81	22656	**8.002**	538.7	23.8	23.0
2	Below SSM Concrete	M25	21/07/2020	28/07/2020	151.26 X 151.10 X 151.63	22856	**8.220**	512.6	22.4	
3	Below SSM Concrete	M25	21/07/2020	28/07/2020	151.09 X 150.51 X 149.81	22741	**8.909**	517.0	22.7	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 18/08/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 23-07-20

Customer ID : Below SSM Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Below SSM Concrete	M25	21/07/2020	18/08/2020	149.61 X 150.20 X 149.36	22470	8.442	616.6	27.4	27.6
2	Below SSM Concrete	M25	21/07/2020	18/08/2020	150.69 X 149.43 X 151.03	22517	8.207	597.2	26.5	
3	Below SSM Concrete	M25	21/07/2020	18/08/2020	150.35 X 150.08 X 151.15	22564	8.732	651.7	28.9	

* The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 28/07/2020

Lab ID : **CP-2020-09-19-62**

Project Name : "Construction of Indoor Stadium with all Amenities at Sahakaranagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division".

Agency : Sri.Abbu Sambasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)/Ynk Zone/WO/114/2017-18

Date of Receipt : 23-07-20

Customer ID : Below SSM Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Below SSM Concrete	M25	21/07/2020	28/07/2020	149.41 X 149.10 X 151.55	22276	**8.002**	534.5	24.0	23.1
2	Below SSM Concrete	M25	21/07/2020	28/07/2020	149.65 X 149.21 X 149.83	22329	**8.220**	502.6	22.5	
3	Below SSM Concrete	M25	21/07/2020	28/07/2020	149.13 X 149.93 X 150.51	22359	**8.909**	511.0	22.9	

* The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |